

ESS.MT.ICE WHITE

FORMATO/ <i>FORMAT</i>	60X120 (F)
ESPESOR/ <i>THICKNESS</i> (mm)	9
PRODUCTO/ <i>PRODUCT</i>	PORCELÁNICO/ <i>PORCELAIN</i>
TIPO/ <i>KIND</i>	ESMALTADO/ <i>GLAZED</i>
GRUPO/ <i>GROUP</i>	Bla - GL

NORMA APLICABLE EN 14411 ANEXO G
APPLICABLE STANDARD ISO 13006 ANNEX G

ENSAYOS/ <i>TESTS</i>	RESULTADOS/ <i>RESULTS</i>
 UNE-EN ISO 10545-2 DIMENSIONES Y ASPECTO SUPERFICIAL  UNE-EN ISO 10545-2 DIMENSIONS AND SURFACE QUALITY	DIMENSIONES CUMPLE CON LA NORMA DIMENSIONS COMPLIES WITH THE STANDARD
 UNE-EN ISO 10545-3 ABSORCIÓN DE AGUA  UNE-EN ISO 10545-3 WATER ABSORPTION	VALOR MEDIO (%) AVERAGE VALUE (%) ≤ 0,5 %
 UNE-EN ISO 10545-4 RESISTENCIA A LA FLEXIÓN  UNE-EN ISO 10545-4 MODULUS OF RUPTURE	FUERZA DE ROTURA BREAKING STRENGTH (N) 1.600 - 2.400 N RESISTENCIA A LA FLEXIÓN MODULUS OF RUPTURE (N/mm ²) 35 - 45 N/mm ²
 UNE-EN-ISO 10545-7 ABRASIÓN SUPERFICIAL (PEI)  UNE-EN-ISO 10545-7 SURFACE ABRASION (PEI)	RESULTADO RESULT PEI IV
 UNE-EN ISO 10545-9 RESISTENCIA AL CHOQUE TÉRMICO  UNE-EN ISO 10545-9 THERMAL RESISTANCE	RESULTADO RESULT RESISTE RESISTS
 UNE-EN-ISO 10545-11 RESISTENCIA AL CUARTEO  UNE-EN-ISO 10545-11 CRAZING RESISTANCE	RESULTADO RESULT RESISTE RESISTS
 UNE-EN ISO 10545-12 RESISTENCIA A LA HELADA  UNE-EN ISO 10545-12 FROST RESISTANCE	RESULTADO RESULT RESISTE RESISTS
 UNE-EN ISO 10545-13 RESISTENCIA QUÍMICA  UNE-EN ISO 10545-13 CHEMICAL RESISTANCE	CLORURO AMÓNICO AMMONIUM CHLORIDE 100 g/l HIPOCLORITO SÓDICO SODIUM HYPOCHLORITE 20 mg/l ÁCIDO CLORHÍDRICO HYDROCHLORIC ACID 3% ÁCIDO CÍTRICO CITRIC ACID 100 g/l HIDRÓXIDO POTÁSICO POTASSIUM HYDROXYDE 30 g/l CUMPLE CON LA NORMA COMPLIES WITH THE STANDARD
 UNE-EN ISO 10545-14 RESISTENCIA A LAS MANCHAS  UNE-EN ISO 10545-14 STAIN RESISTANCE	ÓXIDO VERDE EN ACEITE LIGERO GREEN AGENT IN LIGHT OIL SOLUCIÓN ALCOHÓLICA DE YODO IODINE SOLUTION IN ALCOHOL ACEITE DE OLIVA OLIVE OIL 5 5 5

OBSERVACIONES:

VºBº LABORATORIO:

